

**SC
223**
(June 2008)
(Corr.1 July
2008)
(Corr.2 Apr
2009)

**For Application of SOLAS Regulation II-1/3-2
Performance Standard for Protective Coatings
(PSPC) for Dedicated Seawater Ballast Tanks in
All Types of Ships and Double-side Skin
Spaces of Bulk Carriers, adopted by Resolution
MSC.215(82)**

CONTENT

PSPC 2 Definitions

PSPC 3 General Principles

PSPC 4 Coating Standard

PSPC 4, Table 1: Footnotes of Standards

PSPC 4, Table 1: 1 Design of Coating System

PSPC 4, Table 1: 2 PSP (Primary Surface Preparation)

PSPC 4, Table 1: 3 Secondary Surface Preparation

PSPC 4, Table 1: 4 Miscellaneous

PSPC 5 Coating System Approval

PSPC 6 Coating Inspection Requirements

PSPC 7 Verification Requirements

PSPC Annex 1 Test Procedures for Coating Qualification for Dedicated Seawater Ballast
Tank of All Types of Ships and Double-side Skin Spaces of Bulk Carriers

PSPC Annex 1: Footnotes of Standards

Note:

This UI is to be applied by IACS Members and Associates for ships subject to SOLAS Chapter II-1, Part A-1, Reg.3-2.2, as ~~adopted~~ amended by resolution MSC.216(82) when acting as a recognized organization, authorized by flag State Administrations to act on their behalf, unless otherwise advised, from 1 July 2008.

SC
223
(cont)**PSPC 2 DEFINITIONS**

For the purpose of this Standard, the following definitions apply.

...

2.6 "GOOD" condition is the condition with minor spot rusting as defined in resolution A.744(18).

...

Interpretation

GOOD: Condition with spot rusting on less than 3% of the area under consideration without visible failure of the coating. Rusting at edges or welds, must be on less than 20 % of edges or weld lines in the area under consideration.

Coating Technical File: A term used for the collection of documents describing issues related to the coating system and its application from the point in time when the first document is provided and for the entire life of the ship including the inspection agreement and all elements of PSPC 3.4.

PSPC 3 GENERAL PRINCIPLES

“3.2 Inspection of surface preparation and coating processes shall be agreed upon between the ship owner, the shipyard and the coating manufacturer and presented to the Administration for review. The Administration may, if it so requires, participate in the agreement process. Clear evidence of these inspections shall be reported and be included in the Coating Technical File (CTF) (see 3.4).”

Interpretation

1. Inspection of surface preparation and coating processes agreement shall be signed by shipyard, shipowner and coating manufacturer and shall be presented by the shipyard to the Administration for review prior to commencement of any coating work on any stage of a new building and as a minimum shall comply with the PSPC.
2. To facilitate the review, the following from the CTF, shall be available:
 - a) Coating specification including selection of areas (spaces) to be coated, selection of coating system, surface preparation and coating process.
 - b) Statement of Compliance or Type Approval of the coating system.
3. The agreement shall be included in the CTF and shall at least cover:
 - a) Inspection process, including scope of inspection, who carries out the inspection, the qualifications of the coating inspector(s) and appointment of a qualified coating inspector (responsible for verifying that the coating is applied in accordance with the PSPC). Where more than one coating inspector will be used then their areas of responsibility shall be identified. (For example, multiple construction sites).
 - b) Language to be used for documentation.
4. Any deviations in the procedure relative to the PSPC noted during the review shall be raised with the shipyard, which is responsible for identifying and implementing the corrective actions.
5. A Passenger Ship Safety Certificate or Cargo Ship Safety Certificate or Cargo Ship Safety Construction Certificate, as appropriate, shall not be issued until all required corrective actions have been closed to the satisfaction of the Administration.

“3.4 Coating Technical File

3.4.1 Specification of the coating system applied to the dedicated seawater ballast tanks and double-side skin spaces, record of the shipyard’s and shipowner’s coating work, detailed criteria for coating selection, job specifications, inspection, maintenance and repair shall be documented in the Coating Technical File (CTF), and the Coating Technical File shall be reviewed by the Administration.

3.4.2 New construction stage

The Coating Technical File shall contain at least the following items relating to this Standard and shall be delivered by the shipyard at new ship construction stage:

SC 223

(cont)

- .1 *copy of Statement of Compliance or Type Approval Certificate;*
- .2 *copy of Technical Data Sheet, including:*
 - .2.1 *product name and identification mark and/or number;*
 - .2.2 *materials, components and composition of the coating system, colours;*
 - .2.3 *minimum and maximum dry film thickness;*
 - .2.4 *application methods, tools and/or machines;*
 - .2.5 *condition of surface to be coated (de-rusting grade, cleanliness, profile, etc.); and*
 - .2.6 *environmental limitations (temperature and humidity);*
- .3 *shipyard work records of coating application, including:*
 - .3.1 *applied actual space and area (in square meters) of each compartment;*
 - .3.2 *applied coating system;*
 - .3.3 *time of coating, thickness, number of layers, etc.;*
 - .3.4 *ambient condition during coating; and*
 - .3.5 *method of surface preparation;*
- .4 *procedures for inspection and repair of coating system during ship construction;*
- .5 *coating log issued by the coating inspector, stating that the coating was applied in accordance with the specifications to the satisfaction of the coating supplier representative and specifying deviations from the specifications (example of daily log and non-conformity report (see annex 2));*
- .6 *shipyard's verified inspection report, including:*
 - .6.1 *completion date of inspection;*
 - .6.2 *result of inspection;*
 - .6.3 *remarks (if given); and*
 - .6.4 *inspector signature; and*
- .7 *procedures for in-service maintenance and repair of coating system.*

3.4.3 *In-service maintenance, repair and partial re-coating*

In-service maintenance, repair and partial re-coating activities shall be recorded in the Coating Technical File in accordance with the relevant section of the Guidelines for coating maintenance and repair.

3.4.4 *Re-coating*

If a full re-coating is carried out, the items specified in 3.4.2 shall be recorded in the Coating Technical File.

3.4.5 The Coating Technical File shall be kept on board and maintained throughout the life of the ship."

**SC
223**

(cont)

Interpretation**Procedure for Coating Technical File Review**

- 1 The shipyard is responsible for compiling the Coating Technical File (CTF) either in paper or electronic format, or a combination of the two.
- 2 The CTF is to contain all the information required by the PSPC 3.4 and the inspection of surface preparation and the coating processes agreement (see PSPC 3.2).
- 3 The CTF shall be reviewed for content in accordance with the PSPC 3.4.2.
- 4 Any deviations found under 3 shall be raised with the shipyard, which is responsible for identifying and implementing the corrective actions.
- 5 A Passenger Ship Safety Certificate or Cargo Ship Safety Certificate or Cargo Ship Safety Construction Certificate, as appropriate, shall not be issued until all required corrective actions have been closed to the satisfaction of the Administration.

“3.5 Health and safety

The shipyard is responsible for implementation of national regulations to ensure the health and safety of individuals and to minimize the risk of fire and explosion.”

Interpretation

In order to document compliance with PSPC 3.5, relevant documentation from the coating manufacturer concerning health and safety aspects such as Material Safety Data Sheet is recommended to be included in the CTF for information.

**SC
223**

(cont)

PSPC 4 COATING STANDARD**“4.3 Special application**

4.3.1 This Standard covers protective coating requirements for the ship's steel structure. It is noted that other independent items are fitted within the tanks to which coatings are applied to provide protection against corrosion.

4.3.2 It is recommended that this Standard is applied, to the extent possible, to those portions of permanent means of access provided for inspection not integral to the ship's structure, such as rails, independent platforms, ladders, etc. Other equivalent methods of providing corrosion protection for the non-integral items may also be used, provided they do not impair the performance of the coatings of the surrounding structure. Access arrangements that are integral to the ship structure, such as increased stiffener depths for walkways, stringers, etc., are to fully comply with this Standard.

4.3.3 It is also recommended that supports for piping, measuring devices, etc., be coated in accordance with the non-integral items indicated in 4.3.2.”

Interpretation

Reference is made to the non-mandatory MSC/Circ.1279 "Guidelines for corrosion protection of permanent means of access arrangements", adopted by MSC 84 in May 2008.

**SC
223**

(cont)

PSPC 4 Table 1: Footnotes of Standards*“Footnotes:*

- 5 *Type of gauge and calibration in accordance with SSPC-PA2:2004. Paint Application Specification No.2.*
- 6 *Reference standard: ISO 8501-1:1988/Suppl:1994. Preparation of steel substrate before application of paints and related products – Visual assessment of surface cleanliness.*
- 7 *Reference standard: ISO 8503-1/2:1988. Preparation of steel substrate before application of paints and related products – Surface roughness characteristics of blast-cleaned steel substrates.*
- 8 *Conductivity measured in accordance with ISO 8502-9:1998. Preparation of steel substrate before application of paints and related products – Test for the assessment of surface cleanliness.*
- 9 *Reference standard: ISO 8501-3:2001 (grade P2). Preparation of steel substrate before application of paints and related products – Visual assessment of surface cleanliness. (referred in 3.1).*
- 10 *Reference standard: ISO 8502-3:1993. Preparation of steel substrate before application of paints and related products – Test for the assessment of surface cleanliness. (referred in 3.5).”*

Interpretation

Only the footnoted standards referred to in PSPC Table 1 are to be applied, i.e. they are mandatory.

**SC
223**

(cont)

PSPC 4 Table 1: 1 Design of coating system**“1.3 Coating pre-qualification test**

Epoxy-based systems tested prior to the date of entry into force of this Standard in a laboratory by a method corresponding to the test procedure in annex 1 or equivalent, which as a minimum meets the requirements for rusting and blistering; or which have documented field exposure for 5 years with a final coating condition of not less than “GOOD” may be accepted.

For all other systems, testing according to the procedure in annex 1, or equivalent, is required.”

Interpretation**Procedure for Coating System Approval**

Type Approval Certificate showing compliance with the PSPC 5 shall be issued if the results of either method A+D, or B+D, or C+D are found satisfactory by the Administration.

The Type Approval Certificate shall indicate the Product and the Shop Primer tested. The certificate shall also indicate other type approved shop primers with which the product may be used which have under gone the cross over test in a laboratory meeting the requirements in Method A, 1.1 of this UI.

The documents required to be submitted are identified in the following sections, in addition for all type approvals the following documentation is required:

Technical Data Sheet showing all the information required by PSPC 3.4.2.2.

Winter type epoxy is required separate prequalification test including shop primer compatibility test according to PSPC Annex 1. Winter and summer type coating are considered different unless Infrared (IR) identification and Specific Gravity (SG) demonstrates that they are the same.

Method A: Laboratory Test

1.1 Coating pre-qualification test shall be carried out by the test laboratory which is recognized by the Administration and the test laboratory shall meet the requirements set out in IACS UR Z17.

1.2 Results from satisfactory pre-qualification tests (PSPC Table 1: 1.3) of the coating system shall be documented and submitted to the Administration.

1.3.1 Type Approval tests shall be carried out for the epoxy based system with the stated shop primer in accordance with the PSPC Annex 1. If the tests are satisfactory, a Type Approval Certificate will be issued to include both the epoxy and the shop primer. The Type Approval Certificate will allow the use of the epoxy either with the named shop primer or on bare prepared steel.

1.3.2 An epoxy based system may be used with shop primers other than the one with which it was originally tested provided that, the other shop primers are approved as part of a system, PSPC Table 1: 2.3 and Table 1: 3.2, and have been tested according to PSPC Annex 1, Appendix 1, 1.7, which is known as the “Crossover Test”. If the test or tests are satisfactory, a Type Approval Certificate will be issued. In this instance the Type Approval

**SC
223**

(cont)

Certificate will include the details of the epoxy and a list of all shop primers with which it has been tested that have passed these requirements. The Type Approval Certificate will allow the use of the epoxy with all the named shop primers or on bare prepared steel.

1.3.3 Alternatively the epoxy can be tested without shop primer on bare prepared steel to the requirements of the PSPC Annex 1. If the test or tests are satisfactory, a Type Approval Certificate will be issued. The Type Approval Certificate will just record the epoxy. The certificate will allow the use of the epoxy on bare prepared steel only. If in addition, crossover tests are satisfactorily carried out with shop primers, which are approved as part of a system, the Type Approval Certificate will include the details of shop primers which have satisfactorily passed the crossover test. In this instance the Type Approval Certificate will allow the use of the epoxy based system with all the named shop primers or on bare prepared steel.

1.3.4 The Type Approval Certificate is invalid if the formulation of either the epoxy or the shop primer is changed. It is the responsibility of the coating manufacturer to inform the Administration immediately of any changes to the formulation.

Method B: 5 years field exposure

1.4 Coating manufacturer's records, which shall at least include the information indicated in 1.4.1, shall be examined to confirm coating system has 5 years field exposure, and the current product is the same as that being assessed.

1.4.1 Manufacturer's Records

- Original application records
- Original coating specification
- Original technical data sheet
- Current formulation's unique identification (Code or number)
- If the mixing ratio of base and curing agent has changed, a statement from the coating manufacturer confirming that the composition mixed product is the same as the original composition. This shall be accompanied by an explanation of the modifications made.
- Current technical data sheet for the current production site
- SG and IR identification of original product
- SG and IR identification of the current product
- If original SG and IR cannot be provided then a statement from the coating manufacturer confirming the readings for the current product are the same as those of the original.

1.5 Either class survey records from an Administration or a joint (coating manufacturer and Administration) survey of all ballast tanks of a selected vessel is to be carried out for the purpose of verification of compliance with the requirements of 1.4 and 1.9. The reporting of the coating condition in both cases shall be in accordance with the IACS Recommendation 87, section 2 (IACS Recommendation 87 is not mandatory).

1.6 The selected vessel is to have ballast tanks in regular use, of which:

- At least one tank is approximately 2000 m³ or more in capacity
- At least one tank shall be adjacent to a heated tank and
- At least one tank contains an underdeck exposed to the sun.

1.7 In the case that the selected vessel does not meet the requirements in 1.6 then the limitations shall be clearly stated on the type approval certificate. For example, the coating

**SC
223**
(cont)

cannot be used in tanks adjacent to heated tanks or underdeck or tanks with volume greater than the size surveyed.

1.8 In all cases of approval by Method B, the shop primer shall be removed prior to application of the approved epoxy based system coating, unless it can be confirmed that the shop primer applied during construction, is identical in formulation to that applied in the selected vessel used as a basis of the approval.

1.9 All ballast tanks shall be in "GOOD" condition excluding mechanical damages, without touch up or repair in the prior 5 years.

1.9.1 "Good" is defined as: *Condition with spot rusting on less than 3% of the area under consideration without visible failure of the coating. Rusting at edges or welds, must be on less than 20% of edges or welds in the area under consideration.*

1.9.2 Examples of how to report coating conditions with respect to areas under consideration should be as those given in IACS Recommendation 87.

1.10 If the applied NDFT is greater than required by the PSPC, the applied NDFT will be the minimum to be applied during construction. This will be reported prominently on the Type Approval Certificate.

1.11 If the results of the inspection are satisfactory, a Type Approval Certificate shall be issued to include both the epoxy based system and the shop primer. The Type Approval Certificate shall allow the use of the epoxy based system either with the named shop primer or on bare prepared steel. The Type Approval Certificate shall reference the inspection report which will also form part of the Coating Technical File.

1.12 The Type Approval Certificate is invalid if the formulation of either the epoxy based system or the shop primer is changed. It is the responsibility of the coating manufacturer to inform the Administration immediately of any changes to the formulation.

Method C: Existing Marintek B1 Approvals

1.13 Epoxy based system Coatings Systems with existing satisfactory Marintek test reports minimum level B1 including relevant IR identification and SG, issued before 8 December 2006 can be accepted. If original SG and IR documentation cannot be provided, then a statement shall be provided by the coating manufacturer confirming that the readings for the current product are the same as those of the original.

1.14 The Marintek test report with IR and SG information shall be reviewed and if satisfactory, a Type Approval certificate shall be issued. The certificate shall record the report reference and the shop primer used. The Type Approval Certificate shall allow the use of the epoxy based system either with the named shop primer, unless there is evidence to indicate that it is unsuitable, or on bare prepared steel.

1.15 The epoxy based system approved by this method may be used with other shop primers if satisfactory crossover tests are carried out with shop primers which are approved as part of a system, see Method A, 1.3.2. In this instance, the Type Approval Certificate will include the details of the epoxy based system and a list of all shop primers which have passed these requirements. The Type Approval Certificate will allow the use of the epoxy based system with all the named shop primers or on bare prepared steel.

1.16 Such coatings shall be applied in accordance with PSPC Table 1 rather than the application conditions used during the approval test which may differ from the PSPC, unless

**SC
223**
(cont)

these are more stringent than PSPC Annex 1, for example if the NDFT is higher or high pressure water washing and or sweep blasting of the shop primer is used. In such cases these limiting conditions shall be added to the type approval certificate and shall be followed during coating application in the shipyard.

1.17 The Type Approval Certificate is invalid if the formulation of either the epoxy based system or the shop primer is changed. It is the responsibility of the coating manufacturer to inform the Administration immediately of any changes to the formulation.

Method D: Coating Manufacturer

1.18 The coating/shop primer manufacturer shall meet the requirements set out in IACS UR Z17 paragraphs 4, 5, 6 and 7, (except for 4.6) and paragraphs 1.18.1 to 1.18.6 below, which shall be verified by the Administration.

1.18.1 Coating Manufacturers

- (a) Extent of Engagement – Production of coating systems in accordance with PSPC and this UI.
- (b) These requirements apply to both the main coating manufacturer and the shop primer manufacturer where both coatings form part of the total system.
- (c) The coating manufacturer should provide to the Administration the following information;
 - A detailed list of the production facilities.
 - Names and location of raw material suppliers will be clearly stated.
 - A detailed list of the test standards and equipment to be used, (Scope of approval).
 - Details of quality control procedures employed.
 - Details of any sub-contracting agreements.
 - List of quality manuals, test procedures and instructions, records, etc.
 - Copy of any relevant certificates with their issue number and/or date e.g. Quality Management System certification.
- (d) Inspection and audit of the manufacturer's facilities will be based on the requirements of the PSPC.
- (e) With the exception of early 'scale up' from laboratory to full production, adjustment outside the limitations listed in the QC instruction referred to below is not acceptable, unless justified by trials during the coating system's development programme, or subsequent testing. Any such adjustments must be agreed by the formulating technical centre.
- (f) If formulation adjustment is envisaged during the production process the maximum allowable limits will be approved by the formulating technical centre and clearly stated in the QC working procedures.
- (g) The manufacturer's quality control system will ensure that all current production is the same formulation as that supplied for the Type Approval Certificate. Formulation change is not permissible without testing in accordance with the test procedures in the PSPC and the issue of a Type Approval Certificate by the Administration.

SC 223

(cont)

- (h) Batch records including all QC test results such as viscosity, specific gravity and airless spray characteristics will be accurately recorded. Details of any additions will also be included.
- (i) Whenever possible, raw material supply and lot details for each coating batch will be traceable. Exceptions may be where bulk supply such as solvents and pre-dissolved solid epoxies are stored in tanks, in which case it may only be possible to record the supplier's blend.
- (j) Dates, batch numbers and quantities supplied to each coating contract will be clearly recorded.

1.18.2 All raw material supply must be accompanied the supplier's 'Certificate of Conformance'. The certificate will include all requirements listed in the coating manufacturer's QC system.

1.18.3 In the absence of a raw material supplier's certificate of conformance, the coating manufacturer must verify conformance to all requirements listed in the coating manufacturer's QC system.

1.18.4 Drums must be clearly marked with the details as described on the 'Type Approval Certificate'.

1.18.5 Product Technical Data Sheets must comply with all the PSPC requirements. The QC system will ensure that all Product Technical Data Sheets are current.

1.18.6 QC procedures of the originating technical centre will verify that all production units comply with the above stipulations and that all raw material supply is approved by the technical centre.

1.19 In the case that a coating manufacturer wishes to have products which are manufactured in different locations under the same name, then IR identification and SG shall be used to demonstrate that they are the same coating, or individual approval tests will be required for the paint manufactured in each location.

1.20 The Type Approval Certificate is invalid if the formulation of either the epoxy based system or the shop primer is changed. It is the responsibility of the coating manufacturer to inform class immediately of any changes to the formulation. Failure to inform class of an alteration to the formulation will lead to cancellation of the certificates for that manufacturer's products.

"1.4 Job specification

There shall be a minimum of two stripe coats and two spray coats, except that the second stripe coat, by way of welded seams only, may be reduced in scope where it is proven that the NDFT can be met by the coats applied, in order to avoid unnecessary over-thickness. Any reduction in scope of the second stripe coat shall be fully detailed in the CTF.

Stripe coats shall be applied by brush or roller. Roller to be used for scallops, rat holes, etc., only.

Each main coating layer shall be appropriately cured before application of the next coat, in accordance with coating manufacturer's recommendations. Surface contaminants such as

**SC
223**

(cont)

rust, grease, dust, salt, oil, etc., shall be removed prior to painting with proper method according to the paint manufacturer's recommendation. Abrasive inclusions embedded in the coating shall be removed. Job specifications shall include the dry-to-recoat times and walk-on time given by the manufacturer.

1.5 NDFT (nominal total dry film thickness)⁵

NDFT 320 µm with 90/10 rule for epoxy-based coatings; other systems to coating manufacturer's specifications.

Maximum total dry film thickness according to manufacturer's detailed specifications.

Care shall be taken to avoid increasing the thickness in an exaggerated way. Wet film thickness shall be regularly checked during application. Thinner shall be limited to those types and quantities recommended by the manufacturer."

Interpretation

Wet film thickness shall be regularly checked during application for quality control by the Builder. PSPC does not state who should check WFT, it is accepted for this to be the Builder. Measurement of DFT shall be done as part of the inspection required in PSPC 6.

Stripe coats should be applied as a coherent film showing good film formation and no visible defects. The application method employed should insure that all areas that require stripe coating are properly coated by brush or roller. A roller may be used for scallops, ratholes etc., but not for edges and welds.

**SC
223**

(cont)

PSPC 4 Table 1: 2 PSP (Primary Surface Preparation)

"2. PSP (Primary Surface Preparation)

2.1 *Blasting and profile*^{6,7}

Sa 2^{1/2}; with profiles between 30-75 µm

Blasting shall not be carried out when:

- .1 the relative humidity is above 85%; or*
- .2 the surface temperature of steel is less than 3°C above the dew point.*

Checking of the steel surface cleanliness and roughness profile shall be carried out at the end of the surface preparation and before the application of the primer, in accordance with the manufacturer's recommendations.

2.2 *Water soluble salt limit equivalent to NaCl*⁸

≤ 50 mg/m² of sodium chloride.

2.3 *Shop primer*

Zinc containing inhibitor free zinc silicate based or equivalent. Compatibility with main coating system shall be confirmed by the coating manufacturer."

Interpretation

The conductivity of soluble salts is measured in accordance with ISO 8502-6 and ISO 8502-9, and compared with the conductivity of 50 mg/m² NaCl. If the measured conductivity is less than or equal to, then it is acceptable. Minimum readings to be taken are one (1) per plate in the case of manually applied shop primer. In cases where an automatic process for application of shop primer is used, there should be means to demonstrate compliance with PSPC through a Quality Control System, which should include a monthly test.

Procedure for review of Quality Control of Automated Shop Primer plants

1 It is recognised that the inspection requirements of PSPC 6.2 may be difficult to apply to an automated shop primer plant and a Quality Control approach would be a more practical way of enabling compliance with the requirements of PSPC.

2 As required in PSPC it is the responsibility of the coating inspector to confirm that the quality control procedures are ensuring compliance with PSPC.

3 When reviewing the Quality Control for automated shop primer plants the following procedures should be included.

3.1 Procedures for management of the blasting grit including measurement of salt and contamination.

3.2 Procedures recording the following; steel surface temperature, relative humidity, dewpoint.

SC
223
(cont)

- 3.3 Procedures for controlling or monitoring surface cleanliness, surface profile, oil, grease, dust and other contamination.
- 3.4 Procedures for recording/measuring soluble salts.
- 3.5 Procedures for verifying thickness and curing of the shop primer conforms to the values specified in the Technical Specification.

**SC
223**

(cont)

PSPC 4 Table 1: 3 SSP (Secondary Surface Preparation)**“3.3 Surface treatment after erection⁶**

Butts St 3 or better or Sa 2^{1/2} where practicable. Small damages up to 2% of total area: St 3. Contiguous damages over 25 m² or over 2% of the total area of the tank, Sa 2^{1/2} shall be applied.

Coating in overlap shall be feathered.”

Interpretation

Usually, the fillet welding on tank boundary watertight bulkhead is left without coating on block stage (because not yet be leakage tested), in which case it can be categorized as erection joint (“butt”) to be power tooled to St 3.

“3.6 Water soluble salts limit equivalent to NaCl after blasting/grinding⁸

≤ 50 mg/m² of sodium chloride.”

Interpretation

The conductivity of soluble salts is measured in accordance with ISO 8502-6 and ISO 8502-9, and compared with the conductivity of 50 mg/m² NaCl. If the measured conductivity is less than or equal to, then it is acceptable.

All soluble salts have a detrimental effect on coatings to a greater or lesser degree. ISO 8502-9:1998 does not provide the actual concentration of NaCl. The % NaCl in the total soluble salts will vary from site to site. Minimum readings to be taken are one (1) reading per block/section/unit prior to applying.

**SC
223**

(cont)

PSPC 4 Table 1: 4 Miscellaneous**“4.3 Testing of coating⁵**

Destructive testing shall be avoided.

Dry film thickness shall be measured after each coat for quality control purpose and the total dry film thickness shall be confirmed after completion of final coat, using appropriate thickness gauges (see annex 3).”

Interpretation

All DFT measurements shall be measured. Only the final DFT measurements need to be measured and reported for compliance with the PSPC by the qualified coating inspector. The Coating Technical File may contain a summary of the DFT measurements which typically will consist of minimum and maximum DFT measurements, number of measurements taken and percentage above and below required DFT. The final DFT compliance with the 90/10 practice shall be calculated and confirmed, see PSPC 2.8.

**SC
223**
(cont)**PSPC 5 COATING SYSTEM APPROVAL**

“Results from pre-qualification tests (Table 1, paragraph 1.3) of the coating system shall be documented and a Statement of Compliance or Type Approval Certificate shall be issued if found satisfactory by a third party, independent of the coating manufacturer.”

Interpretation

See Interpretation of PSPC Table 1: 1 Design of coating system, 1.3 Coating prequalification test.

SC 223

(cont)

PSPC 6 COATING INSPECTION REQUIREMENTS

“6.1 General

6.1.1 *To ensure compliance with this Standard, the following shall be carried out by qualified coating inspectors certified to NACE Coating Inspector Level 2, FROSIO Inspector Level III or equivalent as verified by the Administration.*

6.1.2 *Coating inspectors shall inspect surface preparation and coating application during the coating process by carrying out, as a minimum, those inspection items identified in section 6.2 to ensure compliance with this Standard. Emphasis shall be placed on initiation of each stage of surface preparation and coatings application as improper work is extremely difficult to correct later in the coating progress. Representative structural members shall be non-destructively examined for coating thickness. The inspector shall verify that appropriate collective measures have been carried out.*

6.1.3 *Results from the inspection shall be recorded by the inspector and shall be included in the CTF (refer to annex 2 (Example of daily log and non-conformity report)).”*

Interpretation

Procedure for Assessment of Coating Inspectors’ Qualifications

1 Coating inspectors required to carry out inspections in accordance with the PSPC 6 shall be qualified to NACE Coating Inspector Level 2, FROSIO Inspector Level III, or an equivalent qualification. Equivalent qualifications are described in 3 below.

2 However, only coating inspectors with at least 2 years relevant coating inspector experience and qualified to NACE Coating Inspector Level 2 or FROSIO Inspector Level III, or with an equivalent qualification, can write and/or authorise procedures, or decide upon corrective actions to overcome non-compliances.

3 Equivalent Qualification

3.1 Equivalent qualification is the successful completion, as determined by course tutor, of an approved course.

3.1.1 The course tutors shall be qualified with at least 2 years relevant experience and qualified to NACE Coating Inspector Level 2 or FROSIO Inspector Level III, or with an equivalent qualification.

3.1.2 Approved Course: A course that has a syllabus based on the issues associated with the PSPC including the following:

- Health Environment and Safety
- Corrosion
- Materials and design
- International standards referenced in PSPC
- Curing mechanisms
- Role of inspector
- Test instruments
- Inspection Procedures
- Coating specification
- Application Procedures
- Coating Failures

**SC
223**

(cont)

- Pre-job conference
- MSDS and product data sheet review
- Coating technical file
- Surface preparation
- Dehumidification
- Waterjetting
- Coating types and inspection criteria
- Specialized Application Equipment
- Use of inspection procedures for destructive testing and non destructive testing instruments.
- Inspection instruments and test methods
- Coating inspection techniques
- Cathodic protection
- Practical exercises, case studies.

Examples of approved courses may be internal courses run by the coating manufacturers or shipyards etc.

3.1.3 Such a course shall have an acceptable measurement of performance, such as an examination with both theoretical and practical elements. The course and examination shall be approved by the Administration.

3.2 Equivalent qualification arising from practical experience: An individual may be qualified without attending a course where it can be shown that the individual:

- has a minimum of 5-years practical work experience as a coating inspector of ballast tanks during new construction within the last 10 years, and
- has successfully completed the examination given in 3.1.3.

4 Assistant Inspectors

4.1 If the coating inspectors requires assistance from other persons to do the part of the inspections under the coating inspector's supervision, those persons shall be trained to the coating inspector's satisfaction.

4.2 Such training should be recorded and endorsed either by the inspector, the yard's training organisation or inspection equipment manufacturer to confirm competence in using the measuring equipment and confirm knowledge of the measurements required by the PSPC.

4.3 Training records shall be available for verification if required.

**SC
223**
(cont)**PSPC 7 VERIFICATION REQUIREMENTS**

“The following shall be carried out by the Administration prior to reviewing the Coating Technical File for the ship subject to this Standard:

- .1 check that the Technical Data Sheet and Statement of Compliance or Type Approval Certificate comply with this Standard;*
- .2 check that the coating identification on representative containers is consistent with the coating identified in the Technical Data Sheet and Statement of Compliance or Type Approval Certificate;*
- .3 check that the inspector is qualified in accordance with the qualification standards in paragraph 6.1.1;*
- .4 check that the inspector’s reports of surface preparation and the coating’s application indicate compliance with the manufacturer’s Technical Data Sheet and Statement of Compliance or Type Approval Certificate; and*
- .5 monitor implementation of the coating inspection requirements.”*

Interpretation**Procedure for Verification of Application of the PSPC**

- 1 The verification requirements of PSPC 7 shall be carried out by the Administration.
 - 1.1 Monitoring implementation of the coating inspection requirements, as called for in PSPC 7.5 means checking, on a sampling basis, that the inspectors are using the correct equipment, techniques and reporting methods as described in the inspection procedures reviewed by the Administration.
- 2 Any deviations found under 1.1 shall be raised initially with the coating inspector, who is responsible for identifying and implementing the corrective actions.
- 3 In the event that corrective actions are not acceptable to the Administration or in the event that corrective actions are not closed out then the shipyard shall be informed.
- 4 A Passenger Ship Safety Certificate or Cargo Ship Safety Certificate or Cargo Ship Safety Construction Certificate, as appropriate, shall not be issued until all required corrective actions have been closed out to the satisfaction of the Administration.

PSPC Annex 1: TEST PROCEDURES FOR COATING QUALIFICATION FOR DEDICATED SEAWATER BALLAST TANK OF ALL TYPES OF SHIPS AND DOUBLE-SIDE SKIN SPACES OF BULK CARRIERS**Annex 1 Footnotes of Standards**

“Footnotes:

- 10 Reference standard: ISO 2811-1/4:1997. Paints and varnishes. Determination of density.*
- 11 Reference standards: ISO 4628/2:2003. Paints and varnishes – Evaluation of degradation of coatings – Designation of quantity and size of defects, and of intensity of uniform changes in appearance – Part 2. ISO 4628:2003. Paints and varnishes – Evaluation of degradation of coatings – Designation of quantity and size of common types of defect – Part 3: Designation of degree of rusting.*
- 12 Nine equally distributed measuring points are used on panel’s size 150 mm x 150 mm or 15 equally distributed measuring points on panel’s size 200 mm x 400 mm.*
- 13 Reference standard: ISO 4624:2002. Pull-off test for adhesion.*
- 14 Reference standards: ASTM D4145:1983. Standard Test Method for Coating Flexibility of Prepainted Sheet.*
- 16 Reference standard: ISO 6270-1:1998 Paints and varnishes – Determination of resistance to humidity – Part 1: Continuous condensation.”*

Interpretation

Only the footnoted standards referred to in Annex 1 are to be applied, i.e. they are mandatory.

End of Document
