

Guideline No.: J-01 (201510)



# J-01 WELDING CONSUMABLES

Issued date: October 20,2015

© China Classification Society

Foreword:

This Guide is a part of CCS Rules, which contains technical requirements, inspection and testing criteria related to classification and statutory survey of marine products.

This Guide is published and updated by CCS and can be found through <http://www.ccs.org.cn> .  
Comments or suggestions can be sent by email to [ps@ccs.org.cn](mailto:ps@ccs.org.cn) .

Historical versions and release date :

Main changes and effective date:

## CONTENTS

1 Application .....	4
2 Normative references .....	4
3 Plans and documents .....	4
4 Approval test .....	6
5 Unit/batch inspection .....	14

## **WELDING CONSUMABLES**

### **1 Application**

1.1 This Guideline applies to the works approval and unit/batch inspection of the following welding consumables such as electrodes, wires and fluxes intended for use in the welding of metallic structures of ships and relevant products.

- (1) Electrodes for manual arc welding of structural steel
- (2) Wire-flux combinations for submerged arc automatic welding for structural steel
- (3) Wires and wire-gas combinations for semi-automatic and automatic welding of structural steel
- (4) Consumables for use in electro-slag or electro-gas vertical welding of structural steel
- (5) Consumables for use in one-side welding with temporary backing materials of structural steel
- (6) Welding consumables for stainless steel
- (7) Welding consumables for aluminum alloys
- (8) Fluxes.

1.2 The manufacturer of welding consumables such as marine electrodes, wires and fluxes is to obtain works approval by CCS.

1.3 Wire rods and steel tapes for welding consumables are to be supplied by manufacturers recognized by CCS.

### **2 Normative references**

CCS Rules for Materials and Welding.

### **3 Plans and documents**

3.1 The manufacturer of welding consumables is to submit an application for approval, describing clearly the designation (each designation of wire-flux combinations for submerged arc welding; type of gas for gas shielded arc welding wires), specification, grade, level of hydrogen content

(where applicable), applicable welding position, applicable welding current type and/or current polarity.

3.2 The following are to be submitted to CCS for information.

3.2.1 Source of raw materials and technical specification: list of suppliers (such as wire rods, steel tapes and mineral powder) and technical specification of raw materials, such as chemical composition and mechanical properties of wire rods and steel tapes, grain size, appearance, sampling and testing methods of mineral powder.

3.2.2 Information on main production, inspection and test equipment: name, purpose, type (specification), capacity and equipment supplier. The manufacturer is to have appropriate equipment and qualification for unit/batch inspection.

3.2.3 Production and inspection procedure, main technical documents (the coating type, formulation design documents, slag system).

3.2.4 Manufacturer's instructions:

- (1) electrodes: designation (type), grade, purpose, chemical composition and mechanical properties of deposited metal, drying temperature before use, recommended welding parameters;
- (2) wires (solid and flux-cored wires): designation (type), grade, purpose, chemical composition of wires (solid wires), chemical composition of deposited metal (flux-cored wires), mechanical properties of deposited metal, reference data (welding amperage, welding voltage), applicable gas components and gas flow, designation (type) of compatible flux;
- (3) fluxes: designation (type), grade, purpose, type (melted, sintered), slag system, components, current, polarity, drying temperature before application.

3.3 The test program is to be submitted to CCS for approval.

3.3.1 The program may be proposed by the manufacturer and submitted to CCS for approval, or proposed by CCS and confirmed by the manufacturer in written form before execution.

3.3.2 The manufacturer is to clearly state the applicable welding positions of consumables. CCS is to state the approved welding positions in the certificate of works approval, for instance, down hand (F), horizontal (H), vertical upward (Vu), vertical downward (Vd) or overhead (O).

### 3.3.3 Development of test program

- (1) electrodes: the test program is to be developed based on the designation (type), specification and approved grade of the electrodes for approval in accordance with Chapter 1 and Chapter 2 of PART ONE, Chapter 1 and Section 3, 8 and 9 in Chapter 2 of PART THREE of CCS Rules for Materials and Welding respectively;
- (2) wires: the test program is to be developed based on the designation (type), specification and approved grade of the wires for approval in accordance with Chapter 1 and Chapter 2, PART ONE, and Chapter 1 and Section 4, 5, 6, 8 and 9 in Chapter 2, PART THREE of CCS Rules for Materials and Welding respectively;
- (3) fluxes: the test program is to be developed in accordance with Chapter 1 and Chapter 2 of PART ONE, and Chapter 1 and Section 4 in Chapter 2 of PART THREE of CCS Rules for Materials and Welding.

## **4 Approval test**

### 4.1 Place of test

4.1.1 The test samples are to be submitted to independent laboratory approved or recognized by CCS for complete or part test in the following circumstances:

- (1) the initial approval for manufacturer;
- (2) evaluation of the reliability of approval test for manufacturer in present conditions;
- (3) the manufacturer doesn't have conditions for approval test;
- (4) the Surveyor deems necessary.

4.1.2 In addition to the above, where the manufacturer has adequate inspection and test equipment to satisfy the requirements of CCS for effectiveness and accuracy of test result, and has qualified test personnel, the approval test may be carried out in the laboratory of the manufacturer with consent of CCS. In the test items, at least one item for routine (delivery) inspection of relevant consumables is to be carried out in the laboratory of the manufacturer.

### 4.2 Base material for test

4.2.1 For structural steel consumables, the manufacturer is to provide for approval the steel plate

of grade specified in Section 1, Chapter 2 of PART THREE of CCS Rules for Materials and Welding. Selection of a toughness grade lower than that required in the Table may be allowed. The steel plate is to be satisfactorily inspected by CCS. Any grade of marine structural steel may be used for the preparation of deposited metal test assemblies made from the consumables for welding the structural steels. Replacement of plates is to be subject to approval by CCS.

4.2.2 The welding consumables for stainless steel plate are to be selected in accordance with the requirements in Section 8, Chapter 2, PART THREE of CCS Rules for Materials and Welding.

4.2.3 The welding consumables for aluminum alloy plate are to be selected in accordance with the requirements in Section 9, Chapter 2, PART THREE of CCS Rules for Materials and Welding.

4.2.4 In deposited metal test, where the strength or chemical composition of the base material used for approval is different from that of the consumables, transitional layers may be adopted on the prepared edges and surface of backing plates. The thickness of the layer is not to be less than 3 mm. The manufacturer is to submit test assembly diagram and dimension to CCS for approval.

#### 4.3 Preparation of test assembly

4.3.1 The manufacturer is to develop a table indicating the number of test specimens, including designation (type), welding positions, specification and number. The number of test specimen is to be kept from welding of the assembly to finishing of the test specimen, otherwise, the test assembly is to be rejected and a new one is to be welded.

4.3.2 During approval tests, the preparation and testing of the test specimens are to be carried out in the presence of CCS Surveyor. It is recommended that NDT be carried out after welding of test assembly to ascertain that no defect exists in the welds which will affect the accuracy of the tests. After welding, test assemblies are not to be subject to any heat treatment, except the deposited metal longitudinal tensile test specimens. Heat treatment for hydrogen removal is not to be applied to the deposited metal longitudinal tensile test specimens of low hydrogen consumables.

4.3.3 The welding conditions such as amperage, voltage, traveling speed, etc. are to be within the range recommended by the manufacturers. In case of multi-run layers, the direction of deposition of each layer is to change from each end of the plate. The test in the welding of assembly is to be recorded for Surveyor to examine. Where some material is applicable to both alternating current and direct current, the alternating power supply is to be adopted in preparation of specimens.

4.3.4 The test assembly may be restrained or subject to initial distortion prior to welding to prevent angular distortion. Where the warping due to the welding exceeds an angular distortion of 5 degrees, the test assembly is to be discarded. The test assembly after welding is not to be subject

to any straightening (hammered or flattened).

4.3.5 In preparing test assembly, the mark of CCS stamp is to be transferred in the presence of the Surveyor.

4.3.6 The prepared test assembly is to be in accordance with the relevant requirements in PART ONE and PART THREE of CCS Rules for Materials and Welding.

#### 4.4 Test

4.4.1 The test equipment is to have calibration certificate within validity issued by statutory metrological agency.

4.4.2 The proportion of V-notch drawing for check of impact test specimens is to be not less than 50:1. The drawing is to be checked by statutory metrological agency and a calibration certificate is to be provided.

4.4.3 The tensile test, bend test, impact test, fillet weld fracture test, macro-examination and hardness tests in the manufacturer are to be carried out in the presence of the Surveyor. The preparation of hydrogen test specimens and the readings in the manufacturer are to be carried out in the presence of the Surveyor. The specification of the stainless steel specimen for corrosion test is to be examined by the Surveyor. The preparation of corrosive medium and the bending and flattening tests of the specimens are to be carried out in the presence of the Surveyor.

4.4.4 An analysis report of chemical composition of the deposited weld metal (including content of all significant alloy elements) is to be submitted by the manufacturer.

#### 4.5 Approval test items and requirements

4.5.1 The number of electrodes for manual arc welding of structural steel is to comply with the requirements in 2.3.2, PART THREE of CCS Rules for Materials and Welding. Detailed test items and requirements are given in Table 4.5.1. The diameter of electrodes is to be selected in accordance with 2.3.3 and 2.3.4 respectively of PART THREE of CCS Rules for Materials and Welding. In general, two deposited metal test assemblies are to be prepared. One assembly is made with 4 mm diameter electrodes and the other with the largest size manufactured, if electrodes are available in one diameter only, one test assembly is sufficient. The selection of electrodes for down hand butt weld tests is as follows: first run with 4 mm diameter electrode, remaining runs (except the last two layers) with 5mm diameter electrodes. The runs of the last two layers with the largest diameter of the same type of electrode manufactured.

**Test items and requirements for structural steel electrodes for manual arc welding**

**Table 4.5.1**

<b>Serial No.</b>	<b>Test items</b>	<b>Content</b>	<b>Result</b>
1	Deposited metal tests and chemical composition analysis	2.3.3 of PART THREE OF CCS Rules for Materials and Welding	Mechanical properties are to be in accordance with Table 2.2.2.3 of PART THREE of CCS Rules for Materials and Welding; chemical composition analysis is to comply with recognized standards
2	Butt weld tests	2.3.4 of PART THREE OF CCS Rules for Materials and Welding	Mechanical properties are to be in accordance with Table 2.2.2.3 of PART THREE of CCS Rules for Materials and Welding
3	Fillet weld tests	2.3.5 of PART THREE OF CCS Rules for Materials and Welding	In accordance with 2.3.5.3 of PART THREE of CCS Rules for Materials and Welding
4	Hydrogen test (if required)	2.3.6 of PART THREE OF CCS Rules for Materials and Welding	In accordance with Table 2.3.1.1 and Table 2.3.6.3 of PART THREE of CCS Rules for Materials and Welding

4.5.2 The quantities of test assembly for welding consumables for stainless steel are to comply with the requirements in Section 8, Chapter 2, PART THREE of CCS Rules for Materials and Welding. Detailed test items and requirements are given in Table 4.5.2.

**Test items and requirements for welding consumables for stainless steel**

**Table 4.5.2**

<b>Serial No.</b>	<b>Test items</b>	<b>Content</b>	<b>Result</b>
1	Deposited metal tests and chemical composition analysis	2.8.3 of PART THREE OF CCS Rules for Materials and Welding	Mechanical properties are to be in accordance with Table 2.8.3.4 of PART THREE of CCS Rules for Materials and Welding; chemical composition analysis is to comply with recognized standards
2	Butt weld tests	2.8.4 of PART THREE OF CCS Rules for Materials and Welding	Mechanical properties are to be in accordance with Table 2.8.4.3 of PART THREE of CCS Rules for Materials and Welding
3	Fillet weld tests	2.3.5.3 of PART THREE OF CCS Rules for Materials and Welding	In accordance with 2.3.5.3 of PART THREE of CCS Rules for Materials and Welding

**Continued Table 4.5.2**

<b>Serial No.</b>	<b>Test items</b>	<b>Content</b>	<b>Result</b>
4	Measurement of ferrite content of deposited metal	2.8.3.5 of PART THREE OF CCS Rules for Materials and Welding	In accordance with 2.8.3.5 of PART THREE of CCS Rules for Materials and Welding
5	Intercrystalline corrosion test for butt joints	According to Section 7, Chapter 2, PART ONE of CCS Rules for Materials and Welding	

4.5.3 The quantities of test assembly for welding consumables for aluminum alloy are to comply with the requirements in Section 9, Chapter 2, PART THREE of CCS Rules for Materials and Welding. Detailed test items and requirements are given in Table 4.5.3.

**Test items and requirements for welding consumables for aluminum alloy**

**Table 4.5.3**

<b>Serial No.</b>	<b>Test items</b>	<b>Content</b>	<b>Result</b>
1	An analysis of chemical composition of the deposited weld metal	2.9.3.2 of PART THREE OF CCS Rules for Materials and Welding	The report is to include content of all significant elements. The test results are not to exceed the limit values specified by the manufacturer
2	Butt weld test	2.9.3.4 of PART THREE OF CCS Rules for Materials and Welding	Mechanical properties are to be in accordance with Table 2.9.3.7 of PART THREE of CCS Rules for Materials and Welding

4.5.4 The quantities of test specimens for wire-flux combinations for submerged arc automatic welding are to comply with the requirements in Section 4, Chapter 2, PART THREE of CCS Rules for Materials and Welding. Detailed test items and requirements are given in Table 4.5.4.

**Test items and requirements for wire-flux combinations for submerged arc automatic welding**

**Table 4.5.4**

<b>Serial No.</b>	<b>Test items</b>	<b>Content</b>	<b>Result</b>
1	deposited metal test for use with multi-run technique and chemical composition analysis	2.4.3 of PART THREE of CCS Rules for Materials and Welding	Mechanical properties are to be in accordance with Table 2.2.2.3 of PART THREE of CCS Rules for Materials and Welding; chemical composition analysis is to comply with recognized standards

**Continued Table 4.5.4**

<b>Serial No.</b>	<b>Test items</b>	<b>Content</b>	<b>Result</b>
2	Butt weld tests for use with multi-run technique	2.4.4 of PART THREE of CCS Rules for Materials and Welding	Mechanical properties are to be in accordance with Table 2.2.2.3 of PART THREE of CCS Rules for Materials and Welding
3	Butt weld tests for two-run technique	2.4.5 of PART THREE of CCS Rules for Materials and Welding	
4	Hydrogen test (if required) <sup>9</sup>	2.3.6 of PART THREE of CCS Rules for Materials and Welding	In accordance with Table 2.3.1.1 and Table 2.3.6.6 in Section 3, Chapter 2, PART THREE of CCS Rules for Materials and Welding

NOTE: Where welding consumables are intended to be used for high strength steel with a heat treatment of quenching and tempering and the yield stress of 420 N/mm<sup>2</sup> and above, a hydrogen test is to be carried out in accordance with the method approved by CCS.

4.5.5 The quantities of test specimens for wires and wire-gas combinations for semi-automatic and automatic welding is to comply with the requirements in Section 5, Chapter 2, PART THREE of CCS Rules for Materials and Welding. Detailed test items and requirements are given in Table 4.5.5.

**Test items and requirements for wires and wire-gas combinations  
for semi-automatic and automatic welding**

**Table 4.5.5**

<b>Serial No.</b>	<b>Test items</b>	<b>Content</b>	<b>Result</b>
1	Deposited metal tests for semi-automatic multi-run technique and chemical composition analysis	2.5.3 of PART THREE of CCS Rules for Materials and Welding	Mechanical properties are to be in accordance with Table 2.2.2.3 of PART THREE of CCS Rules for Materials and Welding; chemical composition analysis is to comply with recognized standards
2	Deposited metal tests for automatic multi-run technique and chemical composition analysis	2.5.6 of PART THREE of CCS Rules for Materials and Welding	
3	Butt weld tests for semi-automatic multi-run welding	2.5.4 of PART THREE of CCS Rules for Materials and Welding	Mechanical properties are to be in accordance with Table 2.2.2.3 of PART THREE of CCS Rules for Materials and Welding
4	Butt weld tests for automatic multi-run technique	2.5.6 of PART THREE of CCS Rules for Materials and Welding	

**Continued Table 4.5.5**

<b>Serial No.</b>	<b>Test items</b>	<b>Content</b>	<b>Result</b>
5	Butt weld tests for two-run automatic welding	2.5.7 of PART THREE of CCS Rules for Materials and Welding	Mechanical properties are to be in accordance with Table 2.2.2.3 of PART THREE of CCS Rules for Materials and Welding
6	Fillet weld tests for semi-automatic multi-run technique	2.5.5 of PART THREE of CCS Rules for Materials and Welding	In accordance with Table 2.3.5.3 of PART THREE of CCS Rules for Materials and Welding
7	Hydrogen test (if required)	Refer to 2.3.6 of PART THREE of CCS Rules for Materials and Welding	In accordance with Table 2.3.1.1 and Table 2.3.6.6 of PART THREE of CCS Rules for Materials and Welding

4.5.6 The quantities of test specimens for Consumables for use in electro-slag and electro-gas vertical welding is to comply with the requirements in Section 6, Chapter 2, PART THREE of CCS Rules for Materials and Welding. Detailed test items and requirements are given in Table 4.5.6.

**Test items and requirements for consumables for use in electro-slag and electro-gas vertical welding**

**Table 4.5.6**

<b>Serial No.</b>	<b>Test items</b>	<b>Content</b>	<b>Result</b>
1	Butt weld tests	2.6.2 of PART THREE of CCS Rules for Materials and Welding	Mechanical properties are to be in accordance with Table 2.2.2.3 of PART THREE of CCS Rules for Materials and Welding

4.5.7 Test items and requirements for fluxes are given in Table 4.5.7(a).

**Test items and requirements for fluxes**

**Table 4.5.7(a)**

<b>Serial No.</b>	<b>Test items</b>	<b>Result</b>
1	wire-flux combinations for submerged arc automatic welding and wire-flux combinations electro-slag welding	Mechanical properties of deposited metal for wires combined (CCS grade)
2	Grain size	Requirements in Table 4.5.7(b) to be satisfied
3	Content of water	≤ 0.10%
4	Mechanical inclusion	≤ 0.30%
5	Content of sulphur	≤ 0.060%
6	Content of phosphorus	≤ 0.080%

**Requirements for grain size of fluxes**

**Table 4.5.7(b)**

Average size		Fine size	
< 0.450 mm (40 mesh)	≤5%	< 0.280 mm (60 mesh)	≤5%
> 2.50 mm (40 mesh)	≤2%	> 2.00 mm (10 mesh)	≤2%

4.5.8 The test items and requirements for consumables for use in one-side welding with temporary backing materials are given in Table 4.5.8.

**Test items for consumables for use in one-side welding with temporary backing materials**

**Table 4.5.8**

Serial No.	Test items	Content	Result
1	Butt weld test for wire-gas combinations for use with semi-automatic multi-run techniques	2.7.2 of PART THREE of CCS Rules for Materials and Welding	Mechanical properties are to be in accordance with Table 2.2.2.3 of PART THREE of CCS Rules for Materials and Welding
2	Butt weld test for wire-flux combinations (or wire-gas combinations) for use with automatic multi-run techniques		
3	Butt weld test for manual arc electrodes		

4.6 In general, the welding consumables are to be subject to visual examination.

4.7 Approval test report

The works manufacturing the welding consumables are required to submit the approval test report to CCS, which contain the following items:

- (1) test date, environmental conditions and pre-treatment of welding consumables;
- (2) grade, trade mark or brand, type and dimension of the welding consumables;
- (3) material designation, grade, mechanical properties and chemical compositions of test plates;
- (4) welding position;
- (5) welding parameters, the model of welding machines and composition of shielding gas;
- (6) all test results;

(7) welding site records.

**5 Unit/batch inspection**

5.1 After obtaining works approval by CCS, the manufacturer is to apply for unit/batch inspection on the welding consumables for marine use manufactured according to the approved conditions (including equipment, process, etc.).

5.2 Unit/batch inspection is as follows:

**Unit/batch inspection requirements**

**Table 5.2**

Serial No.	Name of consumables	Inspection items
1	Electrodes for manual arc welding of structural steel	(1) examination of quality certificate of wire rods (2) visual examination (3) confirmation of chemical composition of deposited metal (4) deposited metal test (5) additional deep penetration butt welding for electrodes for deep penetration welding in the downhand welding position
2	Wire-flux combinations for submerged arc automatic welding for structural steel	(1) examination of quality certificate of wire rods (2) visual examination (3) confirmation of chemical composition of deposited metal (4) deposited metal test (5) butt welding for wire-fluxes combinations for use only with two-run technique
3	Wires and wire-gas combinations for semi-automatic and automatic welding of structural steel	(1) examination of quality certificate of wire rods (2) visual examination (3) confirmation of chemical composition of deposited metal (4) deposited metal test (5) butt welding test for wires and wire-gas combinations for use with automatic two-run technique
4	Consumables for use in electro-slag and electro-gas vertical welding of structural steel	(1) examination of quality certificate of wire rods (2) visual examination (3) confirmation of chemical composition of deposited metal (4) butt weld test

Continued Table 5.2

Serial No.	Name of consumables	Inspection items
5	Fluxes	(1) visual examination (2) examination of quality certificate of combined wires (3) deposited metal test

5.3 After satisfactory inspection of products, CCS Surveyor is to issue a certificate of marine products or endorse the manufacturer's quality certificate.

5.3.1 The quality certificate is to contain at least the purchaser, acceptance criteria, batch number, approved grade, specification, welding position, mass, quantity, chemical composition, mechanical properties, identification with related description. The space for stamp and endorsement by CCS Surveyor is to be reserved.

5.3.2 The format of the manufacturer's quality certificate is to be approved by CCS.

#### 5.4 Package and identification

5.4.1 All the packages of approved consumables are to be clearly identified with:

- (1) trade mark or brand;
- (2) name or mark of manufacturer;
- (3) approved grade of consumables (and combined consumables for submerged arc welding and gas-shielded welding);
- (4) groups of shielding gases adopted;
- (5) applicable welding current type and/or current polarity;
- (6) applicable welding position;
- (7) manufacturing date and batch number;
- (8) drying temperature;
- (9) Dimension (diameter of welding core, length of electrodes, grain size of fluxes for automatic submerged arc welding).

5.4.2 The welding consumables approved by CCS may be allowed to use the following dedicated logo according to the use license of CCS product approval logo, subject to the requirements given in 3.1.7 of Chapter 3, Part One of China Classification Society Rules for Classification of Sea-Going Steel Ships.



**Figure 5.4.2 CCS Approved Product Logo**