



Guideline No.W-17(201510)

W-17

CLAD STEEL PLATE

Issued date: 20th October 2015

© China Classification Society

Foreword

CCS Product Inspection and Testing Guideline (hereinafter referred to as this Guideline) contains the technical requirements, inspection and testing criteria related to classification and statutory survey of marine products to be applied for CCS approval/inspection.

This Guideline frees the users to adopt other test methods and requirements which are equivalent to or are stricter than this Guideline.

This Guideline is published and updated by CCS, and is released at <http://www.ccs.org.cn>. Your comments or suggestions are welcomed and may be sent to our email addressed mp@ccs.org.cn.

Historical version and release date: W17(201510) October 20, 2015

Main change: New Release

CONTENTS

1 Application4

2 Basis for approval and inspection.....4

3 Plans and documents4

4 Type test7

5 Unit/batch inspection.....9

CLAD STEEL PLATE

1 Application

1.1 This Guideline applies to the works approval and product inspection of clad steel plates produced in accordance with the requirements of *CCS Rules for Materials and Welding* and taking carbon steel and carbon manganese steel as the base layer. If the plates are to be used as a part of the hull structure (such as liquid cargo tank) or for pressure vessels, the base material is to comply with the relevant provisions of the *Rules*.

1.2 This Guideline applies to clad steel plates produced by the explosion method (or other methods).

2 Basis for approval and inspections

The following standards are the bases for works approval and product inspection of rolled steels in this Guideline:

CCS Rules for Materials and Welding

GB/T 8165-2008 *Stainless Steel Clad Plates, Sheets and Strips* and other related national standards

3 Plans and documents

3.1 The organizations going for works approval from CCS are to submit the application to CCS for works approval.

3.2 The applicants are to submit the documents as follows in triplicate for information by CCS:

3.2.1 Factory profile:

Name, address and production history; types and specifications of existing products; types, specifications and delivery conditions of products to be approved; specifications, delivery conditions, chemical compositions and mechanical properties of metal plates (steel grades or designations of base metal and clad metal) forming the products to be approved; and other qualification certificates granted to the factory.

3.2.2 Management documents like quality system management (QMS) document:

- (1) Organizational structure, quality control points, responsibilities of management departments/ managers, quality management system document, identification and traceability management regulations or relevant descriptions;
- (2) For the raw materials processing factory needing to purchase steel plates or other metal plates, procurement and acceptance regulations for raw materials are to be established and the purchasing list of raw materials is to be submitted to CCS. The list is to be issued in the form of official document of the factory, including: names of raw materials, name of the

manufacturer, number of CCS Certificate of Works Approval awarded to the manufacturer, number of factory document, official seal of the factory, etc.

3.2.3 Main production equipment and main inspection/test equipment:

- (1) List of main production equipment including: electric welding machine, cutting machine, hydraulic flattening machine, grinding machine, heat treatment furnace (annealing furnace), etc.;
- (2) List of main inspection/test equipment including: chemical composition analysis equipment, mechanical properties test equipment, nondestructive test equipment, intergranular corrosion test equipment, etc. The inspection/test equipment is to be provided by the manufacturer.

3.2.4 Process documents:

Production process flow chart, control standard for the product type to be approved and process operation instructions (SOP), mainly including:

- (1) Production process flow chart
- (2) Raw material preparation process documents: purchasing standards for base plate and clad plate, including chemical compositions, mechanical properties, dimensions and surface inspection requirements, non-destructive detection standards and surface quality standards;
- (3) Raw material acceptance standard: the raw material is to be inspected and re-tested for relevant items according to corresponding standards or technological requirements. The designation, heat number, dimensions, thickness, surface quality and flatness of incoming material are to be checked against the ordering specifications. Non-destructive detection is to be conducted on the base plate to make sure whether the defect of the clad steel plate arising in subsequent production is caused by the raw material or by the cladding process.
- (4) Cutting process documents for base and clad plates
- (5) Surface treatment process document before explosion cladding
- (6) Cladding process document
 - ① Explosion cladding method
 - (a) Requirements on the face to be fayed are to be checked before explosion cladding;
 - (b) Requirements on the foundation of explosion cladding site;
 - (c) Requirements on the rectangle frame for retaining the explosive;

- (d) Requirements on the lubricating grease on the contact face between the clad plate and the explosive;
 - (e) Requirements on the support between the clad plate and the base plate;
 - (f) Explosion cladding process.
- ② Other methods such as the rolling method
- (a) Stainless steel incoming (components and surface quality inspection);
 - (b) Surface shot blasting of stainless steel (heating process);
 - (c) Assembly rolling process or rolling and welding processes;
 - (d) Composite heating (normalizing and tempering processes);
 - (e) Outline inspection of clad plate; (if passed, the next procedure is to be taken);
 - (f) Rough machining (dimensions inspection; if passed, the product is to be delivered).
- (7) UT: standard and acceptable criterion and index are to be used.
- (8) Heat treatment process document
- ① Heat treatment method (such as stress relief annealing);
 - ② Heating-up temperature and time;
 - ③ Furnace cooling temperature and air cooling time;
 - ④ Heat treatment is one of the important methods to ensure the product properties. In spite of the key role of heat treatment, the proper heat treatment equipment may be selected depending on the factory situation.
- (9) Flattening process document
- (10) Surface treatment process document
- (11) Document of machining and sampling methods for finished products
- (12) Document of inspection method and process for finished products
- (13) Marking, packaging and storage document

3.2.5 Competency certificates of testers and inspectors;

3.3 The type test program is to be submitted to CCS for approval.

3.4 Other documents required by CCS.

4 Type test

4.1 Determination of type test program

Before the type test for works approval, CCS and the applicant are to determine the type test program for the product to be approved through negotiation. The type test program may be proposed by the applicant and is to be acknowledged and approved by CCS; it may also be proposed by CCS and is to be acknowledged by the applicant. The type test program is to include the following content:

- (1) The type, specifications and delivery condition of the product to be approved (the specifications, designations and delivery conditions of corresponding base steel and clad steel are to be specified);
- (2) Information about the type, specifications, quantity and delivery condition of the typical product selected for type test;
- (3) Type test items and applicable rules and standards;
- (4) Sampling position, schematic diagram and sampling instructions;
- (5) Test location and laboratory qualifications (in the case of subcontract, the subcontractor qualifications and subcontract agreement content are to be provided);
- (6) Name of test agency.

4.2 Selection of typical product for type test

Principles for the selection of typical product for type test:

- (1) For the product to be approved, samples are to be taken from the products covering the maximum and minimum processing capabilities for type test. (For example, both the maximum and the minimum specifications are to be selected for the thickness of base steel plate and the thickness of clad metal plate.)
- (2) For clad steel plates formed by different cladding methods, different heat treatment methods or different production methods, alternative sampling methods may not be appropriate.
- (3) The steel plate for the test is to be specified by the Surveyor, and the type test specimens are to be taken at the head and tail of steel plate.

4.3 Type test Items and requirements

See Table 4.3 for the type test items and requirements. The details are as follows:

4.3.1 Chemical composition analysis

The chemical compositions of base plate and clad plate are to be inspected respectively in accordance with the constructions of base steel plate and clad metal plate.

4.3.2 Tensile test

- (1) Full-thickness plates are to be taken as tensile test specimens.
- (2) The tensile test specimens are to be taken longitudinally and transversely, and the determination of the test result is to be based on the CCS Rules.

4.3.3 Bending test

The bending test is to be conducted on both the front and the back respectively in accordance with the CCS Rules or national standards.

4.3.4 V-notch impact test

- (1) The impact test specimen is to be taken at the point close to close to the base material surface; if necessary, the test specimen may be taken from the base material close to the faying face;
- (2) The impact work of V-notch impact test is to be measured and the picture showing the fracture of the impact test specimen is to be provided.
- (3) The requirements on the temperature of the impact test are as shown in Table 4.3.
- (4) If the base steel plate uses the base material of pressure vessel or other materials within the scope of CCS Rules, the test is to be conducted in accordance with the corresponding rules. For the specific test, refer to the *Guideline for the Approval of Rolled Steels*.

4.3.5 Cutting test

The bonding quality of clad metal and base material is to be firstly inspected through UT, and then the cutting property of each layer is to be measured respectively. One transverse cutting test specimen is to be prepared from each steel plate, and tested in accordance with the method approved by CCS. The shear strength of bonding face is to be not less than the following values:

- (1) In the case of the tensile strength $R_m < 280 \text{ N/mm}^2$, the shear strength is to be more than 50% of the tensile strength;

- (2) In the case of the tensile strength $R_m \geq 280 \text{ N/mm}^2$, the shear strength is to be more than 140 N/mm^2 .

4.3.6 Metallographic microstructure

The metallographic picture of the bonding part between layers is to be provided according to the construction of the clad steel plate so as to show the bonding condition between layers of metal. Metallographic structure inspections of 100X and 500X are to be conducted respectively.

4.3.7 Nondestructive test

The bonding quality of clad metal and base material is to be inspected piece by piece through UT. All the areas at least 50 mm away from the surrounding edges are to undergo 100% inspection. The middle area is to undergo continuous inspection along the rectangle loop lines at an interval of 200 mm. The permitted single unbonded area is not to exceed 4000 mm^2 , and the distance between single unbonded areas is not to more than 500 mm.

4.3.8 Intergranular corrosion test

If the stainless steel plate is used for the clad metal plate, the intergranular corrosion test is to be conducted in accordance with the rules.

4.3.9 Dimensions measurement and visual inspection:

- (1) Dimensions measurement and visual inspection are to be conducted piece by piece. The length, width, thickness and diagonal length of each steel plate are to be measured. The thickness is to be measured at least three points in the width direction and at least five points in the length direction. The overall delivery condition is to meet the requirements of the Purchaser;
- (2) The appearance quality is to meet the requirements of the standard.

4.3.10 If the austenitic stainless steel plate is used for the clad steel plate, the intergranular corrosion test is to be conducted on the plate in accordance with the CCS Rules.

The intergranular corrosion test may be conducted in accordance with relevant provisions in the *CCS Rules for Materials and Welding*.

4.3.11 The sampling and mark transfer of type test is to be witnessed by the Surveyor.

5 Unit/batch inspection

5.1 According to the provisions of *CCS Rules for Classification of Sea-Going Steel Ships*, the unit/batch inspection of rolled steels is to be conducted after works approval.

5.2 The factory is to be informed of the detailed requirements on the unit/batch inspection of rolled steels in written form when CCS issues the Certificate of Works Approval.

5.3 The unit/batch inspection of rolled steels is to be conducted in accordance with the approved inspection plan. The inspection plan is to include the inspection and test items to be witnessed, approved and spot-checked. The inspection items are to include mechanical properties witness test (tensile test, impact test, shear test, bending test), nondestructive test, etc.; review of chemical composition analysis report; and spot check of appearance and dimensions. If necessary, the Surveyor may check the process records and inspection records and propose additional test items.

5.4 After completing the product inspection, the CCS Surveyor is to sign and issue a certificate to the qualified product or attach the inspection seal on and sign the certificate of quality.

(1) The certificate of quality is to at least include the acceptance bases (rules, standards and technical agreements), heat/batch number, the type and designation of each layer, size, weight, quantity, delivery condition, chemical compositions, mechanical properties, and product marking description with the reserved space for signature and sealing by the CCS Surveyor.

(2) The format of the certificate of quality is to be approved by CCS

Type approval test items

Table 4.3

Test item	Applicable steel grade and designation	Sampling requirement	Test requirement	Remark
Chemical composition	Each layer of metal plate	Finished product	In accordance with the requirements on each layer of metal	

Continued Table 4.3

Tensile test	Full thickness tensile	1/4 of the width of the head and tail ends, longitudinally and transversely	R_{eH} , R_m , A_5 , RA	
Bending test	Full thickness tensile	1/4 of the width of the head and tail ends, longitudinally and transversely	-	
Impact test (corresponding to the base steel plate)	—	1/4 of the width of the head and tail ends, longitudinally and transversely	Test temperature $^{\circ}m$	
	A,		Grade A: room temperature	
	B,A32/36/40,		Grade B/AH32/AH36: 0	
	D,DH32/36/40,		D,DH32,DH36: -20	
	E,EH32/36/40,		E/EH32/EH36: -40	
	FH32/36/40,		FH32/FH36: -60	
	Other materials specified in the CCS Rules		In accordance with the CCS Rules	
Microstructure	Each layer of metal plate and the bonding part between layers	One end		
Non-destructive detection	Before feeding of each layer of metal plate and after bonding	Each layer of metal plate and the entire clad steel plate		
Miscellaneous	Intergranular corrosion test	One end		When the austenitic stainless steel plate is used for the clad metal plate